



96D Allen Blvd.,  
Farmingdale NY 11735  
TEL: (516)293-8944  
FAX: (516)293-8956

Page 1

Received: 10/05/94	Completed: 10/19/94	Letter: Y	jd	P.O.#: 409107000	Test Report #:	2-05711-0-DU
Client's Identification:		PearlWeave-PREMIUM GRADE				
Tested For: Larry Greenberg Pearlweave Safety Netting, Inc. 606 W 131 Street New York, NY 10027			Key Test: ASTM E 84 Tel: (212) 283-0505 Ext: Fax: (212) 862-8951			

TEST PERFORMED:

ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials

SPECIMEN CONDITIONING:

The item tested was placed in a conditioned atmosphere of 73.4 F +/- 5 F, and 50% +/- 5% RH until equilibrium was reached.

SPECIMEN MOUNTING:

During the test the specimen was held in a horizontal configuration in the ceiling of the test apparatus. The specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.

RESULTS:

Flame Spread Index	Smoke Developed
-----	-----
15	195

REMARKS:

None.

CODE CLASSIFICATION SYSTEM:


	Flame Spread Index	Smoke Developed
-----	-----	-----
Class I or A	0 - 25	450 or Less
Class II or B	26 - 75	450 or Less
Class III or C	76 - 200	450 or Less

CONCLUSION:

Based on the above Results and Code Classification System, the item tested is assigned a:  
 Class I or A rating;  Class II or B rating;  Class III or C rating.

CERTIFICATION:

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM E 84.

  
SIGNATURE OF LABORATORY SUPERVISOR  
THE GOVMARK ORGANIZATION, INC.

jd