



96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: info@govmark.com

Page 1

Received: 03/06/2009	Completed: 03/19/2009	Letter: L1	rb	P.O. #:	Test Report #:	2-77594-1-
Client's Identification	Style: PearlWeave Standard Grade. Content: Polyester. Finish: PVC. Weight (oz/yd <sup>2</sup> ): 2.4. End Use: Safety Netting.					
Tested For: Larry Greenberg Pearlweave Safety Netting, Inc. 606 W 131 Street New York, NY 10027			Key Test: ASTM E 84 (BLDG)			800
			Tel: 1-(212)-283-0505 Fax: 1-(212)-862-8951			Ext:

PC: ME /jd

TEST PERFORMED: ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials \*

APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.024"

PRODUCT CATEGORY:  Textile Type Product  
 Vinyl Type Product  
 Other than Textile Type or Vinyl Type Product:

\* Note: Textile or expanded vinyl wallcoverings classified by this procedure are limited to use in sprinklered areas in certain public occupancies. If textile or expanded vinyl wallcoverings are used in non-sprinklered areas, a room/corner fire test is mandated, such as NFPA 265 for textiles and NFPA 286 for expanded vinyls.

NFPA 286 test method standard applies not only to expanded vinyls, but also to all non-textile products. Therefore, it should be considered for all interior finish applications in non-sprinklered areas.

SPECIMEN MOUNTING:

Adhered: The test specimen was bonded to three 1/4" IRC (Inorganic Reinforced Cement) boards (a cement asbestos substitute) to form a test specimen the face of which was 23" ± 1" x 24'.

Unadhered: The 23" ± 1" x 24' specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.

RESULTS:

Flame Spread Index: 5

Smoke Developed: 115

REMARKS: None.

Received:03/06/2009	Completed:03/19/2009	Letter: L1	rb	P.O. #:	Test Report #:	2-77594-1-
Client's Identification	Style: PearlWeave Standard Grade. Content: Polyester. Finish: PVC. Weight (oz/yd <sup>2</sup> ): 2.4. End Use: Safety Netting.					
Tested For: <b>Larry Greenberg</b>	Key Test: ASTM E 84 (BLDG)					800
Pearlweave Safety Netting, Inc. 606 W 131 Street New York, NY 10027					Tel: 1-(212)-283-0505 Fax: 1-(212)-862-8951	Ext:

CONCLUSION: Based on the above Results and Code Classification System the item tested is assigned a:

Class I or A rating  
 Class II or B rating  
 Class III or C rating  
 Unrated

DATA SUMMARY:

Time to Ignition: 0.02 minutes  
 Maximum Flame Spread "Distance": 1.33 feet  
 Maximum Flame Spread "Time": 0.25 minutes


CODE CLASSIFICATION SYSTEM:

	Flame Spread Index	Smoke Developed
Class I or A:	0 - 25	450 or less
Class II or B:	26 - 75	450 or less
Class III or C:	76 - 200	450 or less

BUILDING CODE CITATION FOR THE CLASSIFICATION SCHEME:

- (1) 2006 edition, NFPA 101 Life Safety Code, para. 10.2.3.4
- (2) 2006 edition, NFPA 5000 Building Construction & Safety Code, para. 10.3.2
- (3) 2006 edition, International Building Code, para. 803.1

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM E 84.



AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC. CT / jb

MS. HEATHER ROBERTSON  
MAR 26 2009

(Page 2 of 2)