



The

Govmark

Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 1

Received: 03/06/2009	Completed: 03/12/2009	Letter: L	rb	P.O. #:	Test Report #:	2-77594-0-
Client's Identification	Style: PearlWeave Standard Grade. Content: Polyester. Finish: PVC. Weight (oz/yd ²): 2.4. End Use: Safety Netting.					
Tested For: Larry Greenberg	Key Test: NFPA 701-2004 TM#2 Flat NC					
Pearlweave Safety Netting, Inc. 606 W 131 Street New York, NY 10027	Tel: 1-(212)-283-0505 Ext: Fax: 1-(212)-862-8951					

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films
- 2004 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially After 72 hours water leaching
 After 3 dry cleanings After 100 hours accelerated weathering
 After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	310
2	0	0	320
3	0	0	340
4	0	0	330
5	0	0	330
6	0	0	340
7	0	0	350
8	0	0	320
9	0	0	330
10	0	0	280

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 105 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes; Fails; Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2004 Edition Test Method #2 Flat Sheet Specimens.

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jb MAR 26 2009 (Page 1 of 2)

Mrs. HEATHER ROBERTSON



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 2

Received: 03/06/2009	Completed: 03/12/2009	Letter: L	rb	P.O. #:	Test Report #:	2-77594-0-
Client's Identification	Style: PearlWeave Standard Grade. Content: Polyester. Finish: PVC. Weight (oz/yd ²): 2.4. End Use: Safety Netting.					
Tested For: Larry Greenberg	Key Test: NFPA 701-2004 TM#2 Flat NC					
Pearlweave Safety Netting, Inc. 606 W 131 Street New York, NY 10027			Tel: 1-(212)-283-0505		Ext:	
			Fax: 1-(212)-862-8951			

PRECONDITIONING: 1 hr @ 220°F (Standard)
 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS:
None.

CONVERSION FACTORS:

mm ÷ 25.4 = inches

g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)