

CLIENT

PEARLWEAVE CORP.

30 Pine Street
NEW ROCHELLE, NY 10801

ATTN: Jeremy Chatoor

SAMPLE IDENTIFICATION:

1. #36 1-7/8" SQUARED MESH BONDED

COLOR: BLACK

FLAMMABILITY

NFPA 701 (2023) TEST 2

FOLDS

		After Flame (Seconds)	Char Length (mm)	Drip Burn (Seconds)	
SPECIMEN *	#1	0.0	235.0	0.0	
	#2	0.0	165.0	0.0	
	#3	0.0	125.0	0.0	
	#4	0.0	240.0	0.0	PASS

* Specimens were conditioned at least 24 hours at 20±5°C before testing.

CRITERIA:

PASS/FAIL

REQUIREMENTS:

CHAR: 1050mm Maximum Individual

DRIP BURN: 2 Seconds Maximum Individual

AFTER FLAME: 2 Seconds Maximum Individual

COMMENTS:

The submitted sample meets the requirements of NFPA 701 (2023) Test 2 Flammability.

TEXTEST

